







VERARBEITUNG VON TEXTILFOLIEN

	 TEMPERATUR	 ZEIT	 DRUCK	 TRÄGER ABZIEHEN	 VORPRESSEN	 WASCHEN
Chemica Flexfolie	160°	20 Sek.	mittel	kalt	2–3 Sek.	max. 90°C
Chemica Flockfolie	160°	15–20 Sek.	mittel	kalt	2–3 Sek.	max. 90°C
Chemica Reflexfolie	160°	10 Sek.	mittel	heiss	2–3 Sek.	max. 60°
Chevron A4	50–160°C	15–20 Sek.	mittel	kalt	2–3 Sek.	40°C
DuoFlex	160°C	20 Sek.	mittel	kalt	2–3 Sek.	40°C
Fashion Folien A4	165°C	15 Sek.	mittel	kalt	2–3 Sek.	40°C
Flex Metallic	145°C	15 Sek.	mittel	kalt	2–3 Sek.	40°C
Flex nachleuchtend	150–160°C	15–18 Sek.	mittel, 3.5 bar	warm	2 Sek.	40°C
Flexfolie (Poli-Flex)	155–165°C	17–20 Sek.	mittel, 3.5 bar	warm	2 Sek.	60°C
Flexfolie Fashion: Jeans, Leopard, Zebra	155–165°C	17–20 Sek.	mittel, 3.5 bar	kalt	2 Sek.	40°C
Flexfolie Fashion: Stripes, Techno, Leder	155–160°C	15–20 Sek.	mittel, 3.5 bar	kalt	2 Sek.	60°C
Flexfolie gold/silber	155–165°C	17–20 Sek.	mittel, 3.5 bar	kalt	2 Sek.	40°C
Flexfolie Paint	155–165°C	17–20 Sek.	mittel, 3.5 bar	warm	2 Sek.	60°C
Flexfolie Siser	150°C	15 Sek.	mittel, 3.5 bar	kalt oder warm	2–3 Sek.	80°C
Flexfolie Siser Stretch	155°C	15 Sek.	mittel, 3.5 bar	kalt oder warm	2–3 Sek.	60°C
Flexfolie Starflex	150–160°C	15–18 Sek.	mittel, 3.5 bar	kalt	2 Sek.	40°C
Glitter-Flex	160°C	15 Sek.	mittel, 2.5–3 bar	warm	2 Sek.	60°C
HappyFlex Chameleon	150°C	10 Sek.	mittel	kalt	2–3 Sek.	40°C
HappyFlex MagicMelt	150°C / 130°C	5 Sek. / 10 Sek.	mittel	kalt	2–3 Sek.	40°C
HappyFlex Vintage deckend	160°C	10 Sek.	mittel	kalt	2–3 Sek.	40°C
HappyFlex Vintage Vintage-Effekt	200°C	20 Sek.	hoch	heiss	2–3 Sek.	40°C
HappyPrint Dark	175°C - 185°C (Laserdrucker) 185°C - 195°C (Tintenstrahldrucker)	25 Sek.	mittel	kalt	2–3 Sek.	40°C
Pearl Glitter	155–165°C	17–20 Sek.	mittel, 3.5 bar	warm	2 Sek.	60°C
Politape Turbo Flexfolie	130°C 150°C	5 Sek. 4 Sek.	mittel, 3.5 bar	kalt oder warm	2–3 Sek.	60°C
Reflexfolie	155–165°C	17–20 Sek.	mittel, 3.5 bar	warm	2 Sek.	60°C
TrikotFlex für Polyester	130°C	15 Sek.	mittel, 3.5 bar	warm oder kalt	1 Sek.	60°C
Textilfolien littlefeet (Eigenproduktionen gemustert)	150–160°C	15–20 Sek.	mittel	kalt	2–3 Sek.	40°C
Videoflex Moda Glitter	150°C	15 Sek.	mittel, 3.5 bar	kalt	2–3 Sek.	40°C